

EP04/12189 21.1185



EP04/12189




INVESTOR IN PEOPLE

**PRIORITY
DOCUMENT**
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ


I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.



In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.




Signed

Dated 29 December 2004

BEST AVAILABLE COPY

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)



The Patent Office

Cardiff Road
Newport
South Wales
NP9 1RH

1. Your reference

GB 21.1185

2. Patent application number

(The Patent Office will fill in this part)

0324967.9

27 OCT 2003

3. Full name, address and postcode of the or of each applicant (underline all surnames)

SCHLUMBERGER HOLDINGS LIMITED

723 6326001

LE CENTRE NATIONAL DE LA RECHERCHE
SCIENTIFIQUE

8741209001

Patents ADP number (if you know it)

If the applicant is a corporate body, give the country/state of its incorporation

4. Title of the invention

HIGH TEMPERATURE CEMENTS

5. Name of your agent (if you have one)

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

Brian STOOLE
SENSA, Gamma House, Enterprise Road
Chilworth Science Park, Southampton
Hampshire SO16 7NS,
England

8418733001

Patents ADP number (if you know it)

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number
(if you know it)

Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

YES

- a) any applicant named in part 3 is not an inventor, or
 - b) there is an inventor who is not named as an applicant, or
 - c) any named applicant is a corporate body.
- See note (d))

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form 3
Description 11
Claim(s) 2
Abstract 1
Drawing(s) 13

13 RM

10. If you are also filing any of the following, state how many against each item.

Priority documents 0
Translations of priority documents 0
Statement of inventorship and right to grant of a patent (Patents Form 7/77) 1
Request for preliminary examination and search (Patents Form 9/77) 1
Request for substantive examination (Patents Form 10/77) 1

Any other documents (please specify)

Additional Applicant sheet, Fee Sheet, Cover Letter,

11.

I/We request the grant of a patent on the basis of this application.

Signature

[Signature]

Date

October 22, 2003

Martin HYDEN Chartered Patent Agent

12. Name and daytime telephone number of person to contact in the United Kingdom

Brian STOOLE
02380 765573

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.*
- Write your answers in capital letters using black ink or you may type them.*
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.*
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.*
- Once you have filled in the form you must remember to sign and date it.*
- For details of the fee and ways to pay please contact the Patent Office.*

Patents Form 1/77

Continuation Form 1/77

APPLICANTS Sheet : O/Ref. GB 21.1185

First Applicant

Name :	SCHLUMBERGER HOLDINGS LIMITED
Address :	PO BOX 71 Craigmuir Chambers Road Town – Tortola
Country :	British Virgin Islands

Second Applicant

Name :	LE CENTRE NATIONAL DE LA RECHERCHE SCIENTIFIQUE
Address :	3, rue Michel Ange 75016 Paris
Country :	FRANCE

HIGH TEMPERATURE CEMENTS

The present invention relates to cement compositions for high-temperature applications, and to methods for designing such compositions and to articles made from such compositions. In particular, the invention provides silico-aluminous modified Portland cement for high temperature applications and fire safety protection.

WO 03/068708 describes techniques for producing cement compositions capable of withstanding relatively high temperatures, involving determination of the temperature to which the slurry will be exposed in situ; determination of a stable, thermodynamic equilibrium composition of a $\text{CaO-Al}_2\text{O}_3\text{-SiO}_2\text{-H}_2\text{O}$ (CASH) mineral system, analogous to the cement when set, at the determined temperature; determining proportions of cement and mineral oxides required to provide a mixture having the determined composition; and defining a series of particulate materials of predetermined particle sizes and densities, comprising cement and mineral oxides in the determined proportions. One suitable range of compositions falls in the Margarite-Quartz-pectolite region of the Si-Ca-Al (Na) phase diagram and optimizes early formation of Anorthite. Such compositions often involve the use of kaolin, metakaolin and/or calcination products of metakaolin, and are suitable for use at temperatures in the range $250^\circ\text{C} - 900^\circ\text{C}$.

EP 0 922 013 proposes compositions suitable for certain high temperature applications which promote the formation of calcium hydrogarnets from the series $[\text{SiO}_4]\text{Ca}_3\text{M}^{3+}$, where $\text{M} = \text{Al}$ (grossular) or $\text{M} = \text{Fe}$ (andradite).

WO 01/70646 proposes cement compositions to provide a cement matrix in the Si-Ca-Al triangle in one of the margarite-haüyne-[epidote/pumpellyite], haüyne-prehnite[epidote/pumpellyite] and haüyne-prehnite-pectolite composition triangles. Such compositions are proposed as suitable for use in conditions of elevated temperature and pressure ($250^\circ\text{C} - 300^\circ\text{C}$; 20MPa).

Other approaches to the problems of high temperature cements can be found in US 4,642,137; US 4,877,452; US 4,935,060; US 5,158,613; US 5,900,053; US 6,143,069; US 6,332,921; US 6,367,556; and US 6,488,763.

EP 0 621 247 describes cement compositions having high solids content while being able to form stable slurries. WO 01/09056 describes the application of this technology to low density slurries.

The degradation mechanisms of cement when exposed to high temperatures are relatively well-known, and are addressed, in part, by the proposals summarized above. Up to 400°C, the main stable cement phases are hydrous. Thus, when presented with fast heating rates and very high temperatures and intensities (for example such as those found in hydrocarbon fires), such cements undergo spalling caused by the explosive effect of the increase in pore water pressure generated by the dehydration of the minerals, and due to the saturation vapour pressure due to the inherent moisture content of the cement. In such cases, major physical damage occurs to the cement, often leading to failure of the structure of which it is part.

In the construction industry, the approach to heat resistance is often to use heat-resistant aggregates in the cement in an attempt to stabilise the set cement when exposed to very high temperatures. However, since the cement matrix is unchanged, the problems of degradation and spalling still occur.

The present invention seeks to provide cement compositions in which the conditions leading to degradation such as spalling at high temperatures is reduced or avoided.

In accordance with one aspect of the present invention, there is provided a cement composition comprising a mixture of cement and minerals contributing silicon, calcium and aluminium (with possible contribution of iron and magnesium) to the mixture, wherein the composition of the mixture lies substantially in the [xonotlite/wollastonite]-grossular-anorthite or grossular-anorthite-quartz triangles of the Si-Ca-Al phase diagram.

Articles according to the invention comprise pre-cast units made from a cement composition according to the invention and subjected to curing under elevated temperature.

A method of designing a cement composition according to the invention comprises determination of the temperature to which the composition will be exposed in situ; determination of a stable, thermodynamic equilibrium composition of a $\text{CaO-Al}_2\text{O}_3\text{-SiO}_2\text{H}_2\text{O}$ (CASH) mineral system (with possible contribution of FeO and MgO) in the [xonotlite/wollastonite]-grossular-anorthite or grossular-anorthite-quartz triangles of the Si-Ca-Al phase diagram, analogous to the cement when set, at the determined temperature; determining proportions of cement and mineral oxides required to provide a mixture having the determined composition; and defining a series of particulate materials of predetermined particle sizes and densities, comprising cement and mineral oxides in the determined proportions.

The present invention resides in the recognition that rocks known as skarns which are extremely stable at high temperatures and have compositions that are similar to those that can be obtained by combining cement and mineral oxides. Skarns are rocks resulting from granitic magma intrusion inside carbonate layers. These high temperature conditions ($500 - 700^\circ\text{C}$) combined with silicon and aluminum contribution, transform the initial mineralogy of carbonate layers into high temperature stable rocks formed by anhydrous calco-silicates and calco-alumino-silicates, such as wollastonite, anorthite, grossular, diopside and idocrase, with the remains of the initial formation carbonates in various proportions depending on the temperature reached. The present invention is based on the recognition that it is possible to obtain skarn-like compositions by modifying the chemical composition of Portland cement by the inclusion of mineral oxides. In doing so, the problems of the pervious technique are addressed since the cement matrix becomes heat resistant and so less susceptible to heat degradation. The invention also has the advantage that it can be implemented in a number of forms allowing pumping, spraying and formation or pre-cast articles.

Compared to a Portland cement the skarn bulk composition is mainly characterized by and alumina and silica enrichment. As skarns can be considered as a high temperature stable model material, the Portland cement formulations are modified according to the invention by the addition of mineral oxides to reach the skarn bulk composition.

The proportions of cement and mineral oxides required to form a stable cement can be determined from general thermodynamic rules, phase relations between minerals and fluids and minerals, activity models and homogenous and heterogeneous phase equilibria known and developed for natural silicon- and calcium-rich rock systems of various origin to predict the mineralogy and chemical behaviour of Portland cements or derived compounds set in environments comparable to those encountered in geological settings such in metamorphism, plutonism and volcanism, as has been proposed previously in WO03/068708 for other cement compositions. Consequently, for a compositional system close to the desired Si-Al-Ca system, the main targeted minerals are anorthite, grossular (garnet) with as possible others minerals like wollastonite or other very high temperature anhydrous minerals stable at high temperature in the considered system like melilite. In presence of iron and magnesium, mineral of the FeO-Fe₂O₃-MgO-CaO-SiO₂-Al₂O₃-H₂O can appear in high temperature conditions like pyroxene of the diopside-hedenbergite or garnet solid-solutions as shown in Figure 1.

The method provides cement slurries or grout compositions that promote anorthite formation above 250°C, during the hydration of cement slurry, by adding specific modifiers containing aluminum and silicon in stoichiometric proportions. If the set cement is heated at higher temperatures, up to 1200°C, anorthite, calcium rich garnet (grossular,) and wollastonite, become the main stable binders of set cement as observed in some skarns in high temperature geological contexts. This process can be used to create temperature-resistant articles made from cement in accordance with the invention.

However, the physics of optimizing the packing between the different particles used to modify Portland cement composition has to be mastered to control the final set cement permeability and density. The particle size distribution of each component is optimized to obtain a high packing volume fraction and hence a high solids content to the composition. For example, the solid components can be provided in three or more distinct particle size fractions to optimize the amount of solids in the mixture. This technique allows the use of large amounts of solids while making the slurry still easily pumpable. The methods described in EP 0 621 247 can be followed to achieve this.

Portland cement can conveniently be used as the hydraulic binder, although other forms of cement or reactive hydraulic binders such as slag materials can also be used. Cenospheres or other hollow particulate material of very low density (0.7 to 0.8 sg or lower) can be added to decrease the slurry density. The use of this hollow material allows the formation of a porous structure permitting easier escape of vapor pressure when the temperature increases. These hollow particles also contribute to the modification of Portland cement bulk composition to reach the target formulation by virtue of their chemical composition (typically being aluminosilicate materials). Silica flour and other aluminum modifiers can be also added to finally reach the desired bulk composition.

As well as temperature-resistance, cement compositions according to the present invention can be provided which demonstrate considerably lower pH than conventional cements, i.e. as low as pH 8.5. Such cements can be particularly useful in situations which encounter relatively low pH environments (e.g. pH < 7) in which the highly basic nature of conventional cements can cause problems due to reactivity.

The present invention will now be described by way of examples, with reference to the accompanying drawings, in which:

Fig 1 shows mineral phases known to be stable in natural calcium-rich systems plotted of in the $\text{CaO-Al}_2\text{O}_3\text{-SiO}_2$ ternary diagram (H_2O in excess, FeO and MgO possibly present);

Figs 2a and 2b show certain stable mineral phases, examples of compositions of the present invention and comparative examples in the $\text{CaO-Al}_2\text{O}_3\text{-SiO}_2$ ternary diagram;

Figs 3 shows the liquidus surface and compatibility relations of the $\text{CaO-Al}_2\text{O}_3\text{-SiO}_2$ and CaO-MgO-SiO_2 system for different assemblages;

Figure 4 shows the liquidus surface in the $\text{CaO-Al}_2\text{O}_3\text{-SiO}_2$ system for an addition of 5% MgO ;

Figure 5 shows a plot of the strengths of the cement compositions according to the invention compared to those of prior art cements;

Figures 6 – 18 show photographs of cement samples after being subjected to various temperatures over periods of time; and

Figures 19 – 29 show micrographs of various cement samples.

Fig. 1 shows mineral phases known to be stable in natural calcium-rich systems plotted of in the $\text{CaO-Al}_2\text{O}_3\text{-SiO}_2$ ternary diagram (H_2O in excess, FeO , Fe_2O_3 and MgO possibly present). These comprise:

- anhydrous mineral stable at high temperature: xonotlite/wollastonite, grossular (and the almandin-andradite-pyrope-solid-solution), anorthite, melilite, Larnite (clinker phase);
- moderately hydrous minerals stable at medium temperature: wairakite, prehnite, epidote, margarite, vuagnatite, portlandite;
- conventional phase encountered in cement when submitted to low and medium temperature conditions: truscotite/bredigite, tobermorite, C_2HS ; and
- low and high temperature minerals from the Fe-Mg-Si-Al-Ca system projected in the Si-Al-Ca plane and liable to appears if Fe and Mg are present: truscotite/bredigite, diopside/hedenbergite, merwinite, vesuvianite, melilite.

Class G cement is also plotted for reference.

Figure 2a shows possible stable phase relations in the considered system for different temperature conditions :

- wairakite-grossular-anorthite assemblage (X) stable at moderate temperature conditions (250-350°C);
- wollastonite-grossular-anorthite (Y), and quartz-grossular-anorthite (Z) assemblages stable in high temperature conditions 350-900°C; and
- wollastonite-melilite-anorthite assemblages stable at higher temperature conditions up to 1200°C (W)

Figure 2b plots tested formulations #2, #3, #4 and #5 with respect to assemblages X, Y and Z.

Figure 3 shows the liquidus surface and compatibility relations of the $\text{CaO-Al}_2\text{O}_3\text{-SiO}_2$ and CaO-MgO-SiO_2 systems showing the temperature of the appearance of the last melting in the solid for different assemblages (after phase diagrams for Ceramist : American Ceram. Soc. 1956; 1964, 1969 in Slag Atlas 1995 Verlag Stahleisen GmbH, D-Düsseldorf). The pure anorthite melting point is located at 1265°C while the first melting in the solid appears at 1170°C for silica rich compositions (crystalite-wollastonite-anorthite assemblage) and 1265 °C for more alumina rich compositions

(anorthite-melitite (gehlenite)-wollastonite assemblages) compatible with the more aluminous cements compositions shown figure 2.

Figure 4 shows the effect of an adding of 5% in weight of MgO in the system CaO-Al₂O₃-SiO₂ and the resulting change in mineralogy along the liquidus (after Cavalier, Sandreo-Dendon 1960 in Slag Atlas 1995 Verlag Stahleisen GmbH, D-Düsseldorf).

Figure 5 shows the strengths of the new modified Portland cement according to the invention compared to the ones obtained with high-alumina cement concretes made with anorthosite aggregates, as a function of temperature. The cement according to the invention, without aggregates, shows an equivalent tendency for temperatures up to 500°C than the concrete already optimized for high temperature application in the construction using temperature-resistant aggregates.

Various cement blends are prepared to demonstrate the present invention.

Table 1 summarizes the blend composition (ratio Si/Al/Ca), the slurry density, the water/cement ratio and the solids volume fraction (porosity).

All slurry properties are measured as per API specifications (API Recommended Practice for testing Oil-Well Cements and cement Additives (1990) API Spec.10 Fifth Edition (07.01.1990)).

The compositions of blends #0, #2, #3, #4 and #5 in the quaternary system (CaO-SiO₂-Al₂O₃-H₂O) are shown in Figure 2b.

Table 1: Properties of the slurries

No. slurry	#0	#3	#4	#5	#2
Ratio Si/Al/Ca	47/3/50	51/13/36	48/20/33	50/30/20	44/32/24
Density (g.cm ⁻³)	1.84	1.49	1.49	1.49	1.74
Water/Cement ratio	0.5	0.79	0.72	0.86	1.34

Solids Volume Fraction %	41	54	59	55	41
Free Water	0	0	0	0	0
Blend	Cement Silica flour - -	Cement Silica flour Cenospheres -	Cement Silica flour Cenospheres Aluminum modifier	Cement Silica flour Cenospheres Aluminum modifier	Cement Silica flour - Aluminum modifier

The slurries are mixed following the API procedure. Mixing is done in a Warring Blender. All solid components are dry blended before being added to the water containing the liquid additives.

Once the slurry design has been optimized, samples are prepared for curing by pouring the mixed slurry into a 5cm x 5cm x 5cm steel molds. Five cubes are prepared for each formulation. The molds containing the slurries are cured for three days at 150°C over 21 MPa in a standard oil well cement-curing chamber in water. The temperature is gradually increased to 300°C over a 6-8 hour heat up period, to minimize possible cracking of the samples due to thermal expansion. The temperature is maintained at 300°C over 21 MPa for 5 or 28 days, after which the system is allowed to cool down to room temperature. Samples are then removed, kept under water at room temperature before being tested for the following physical property measurements. The Uniaxial compressive strength is performed on 2.5 x 5 cm cores in using a load frame.

Samples are also cured in high temperature refractory furnace at different temperatures up to 1200°C. In order to demonstrate the benefits of the present invention, two compositions are selected having substantially the same density, same particles and similar porosity: 51/13/36- #3 (comparative example) and one close to the recommended compositions, and 48/20/32- #4 (present invention). Mineralogical examination is carried out by x-ray powder diffraction using CuK α radiation. Scanning Electron Microscope images are used to describe morphologies of reaction products and to complete the XRD analysis.

The results of the mineralogical composition of the different samples are presented in the following table 2.

Formulation Number	#0	#3	#4		#5	#2
Ratio Si/Al/Ca	47/3/50	51/13/36	48/20/32		50/30/20	44/32/24
Density g/cm ³	1.84	1.49	1.49		1.49	1.73
Aluminum modifier type	-	-	A	B	B	B
Xonotlite C ₆ S ₆ H	++++	++++	+	ε	ε	ε
Anorthite CaAl ₂ Si ₂ O ₈	-	ε	++	+++	+++	+++
Truscotite	-	-	-	+	-	-
Wairakite	-	-	+	-	-	-
Quartz SiO ₂	-	-	-	-	+	ε
Corundum μAl ₂ O ₃	-	-	-	-	-	-
Compressive Strength (MPa,psi) at 300deg.C after 5 days	13.5 (1960)	-	-	38 (3147)	38 (5511)	11.1 (1610)
after 28 days	32 (4600)	17.3 (2500)	14.5 (2100)	18 (2600)	18(2600)	-

++++ Prevailing phase; +++ phase in appreciable amount; ++ phase in fairly good amount; + phase in small amount.

The set cement cores from blends #3 and #4 are cured one month at 300 °C are then cut as smaller samples and cured in high temperature furnace. The set cement sample from blend #4 has been observed and analyzed by XRD and SEM (Xray analysis and BSE imaging) after different curing durations. Figures 6 – 18 are photographs of the set cement from the two blends. #3 and #4 after curing at 300 °C (58 days), 600 °C (9 days), 750 °C (30 days), 900 °C (9 days) and 1200°C (9 days) are presented.

Figures 6 and 7 show #4 and #3 after 58 days at 300 °C. For the system #3, cracks and many deleterious signs are well observed after 2 months at 300 °C in the refractory furnace. For the new system from the slurry #4, integrity is maintained.

Figure 19 is a micrograph of a thin section cut in set cement from blend #4 after 58 days at 300 °C, showing general high porosity, cenosphere relics and anorthite as main binder forming the wall of cenosphere and the matrix. Figure 20 shows details of this micrograph showing an anorthite cenosphere and assemblage anorthite- garnet (grossular-andradite) growing inside wairakite crystal relic. Figure 21 is a close-up on anorthite overprint inside wairakite crystal.

Figures 8 and 9 show corresponding samples after 9 days at 600 °C. The set cement sample #4 is cut again with a small saw. Very consistent slices are obtained and no sign of degradation is observed even after one week at 600 °C (Fig 8). Anorthite and garnet are the main binders and wairakite disappears. Figure 22 is a micrograph showing garnet in the set cement matrix after one week at 600 °C. For #3, the set cement sample is completely disintegrated and friable and it is not possible to saw it as it has been done with #4 (Fig 9).

Figures 10 and 11 show corresponding samples after 9 days at 750 °C. Again, #4 maintains its integrity, unlike #3.

Figures 12, 13 and 14 show corresponding samples after 9 days at 900 °C. Figure 12 show the entire sample #4 and Figure 13 the sample after cutting. The sample maintains good integrity and can be cut without splitting. Anorthite and wollastonite remain the main binders, and garnet is still present. Figures 23 and 24 show a micrograph (BSE imaging) of a thin section cut in set cement from blend #2 after 9 days at 900 °C showing anorthite in set cement matrix and in the wall of hollow microspheres (Fig. 24). Figures 25 and 26 show close-up (SE imaging) of some hollow microspheres in the same sample constituted by a pyroxene of the hedenbergite-diopside solid-solution. Figure 14 shows #3 which has many cracks and deterioration signs and color variations.

Figures 15 and 16, and 17 and 18 show corresponding samples after 9 days at 1200 °C. #4. Figures 15 and 16 shows that the sample #4 maintains its integrity with a high hardness despite of some signs of melting and some size reduction. Anorthite is still the main binder. Wollastonite and garnet grossular are also observed together with glass. Figure 27 is a micrograph (SE imaging) of thin section of set cement from blend #4 after one week at 1200 °C showing the hollow sphere relics and the good

remaining integrity of the new formulation even at 1200 °C. Figure 28 is a micrograph (SE imaging) showing anorthite and glass in the matrix with a wollastonite crystal (stars are artifacts due to the sample preparation for SEM examination.) As predicted, the first melting appears in this sample heated one week at 1200 °C. Figure 29 shows garnet-grossular crystal at the surface of the sample and covered by anorthite crystals covered in glass. Figures 17 and 18 shows sample #3 severely damaged due to melting after 9 days at 1200 °C.

The composition of cements according to the present invention between 300 and 1200 °C is mainly anorthite. At 300 °C, anorthite is the main binder with wairakite present with the initial aluminum modifier. The presence of wairakite is related to the reaction kinetic due to the aluminum modifier reactivity.

The very high temperatures curing performed in air inside a refractory furnace and shows the good stability of the compositions according to the invention even at very high temperature. This stability is principally due to the presence of anorthite which is known to begin to melt only at around 1265 °C.

The present invention provides mixable lightweight formulations having good mechanical properties which can use conventional Portland cement for temperatures up to 1200°C and more if modified using the former rules. As these formulations are based on conventional Portland cements good workability can be obtained using techniques widely found in the construction and well cementing industries. Also, parts can be precast using known techniques.

CLAIMS

- 1 A cement composition comprising a mixture of cement and minerals contributing silicon, calcium and aluminium, and optionally iron and/or magnesium, to the mixture, wherein the composition of the mixture lies in the [xonotlite/wollastonite]-grossulaire-anorthite or grossulaire-anorthite-quartz triangles of the Si-Ca-Al phase diagram.
- 2 A composition as claimed in claim 1, wherein solid components are provided in three or more distinct particle size fractions.
- 3 A composition as claimed in claim 1 or 2, wherein the cement comprises Portland cement.
- 4 A composition as claimed in claim 1, 2 or 3, further comprising at least one hollow particulate material.
- 5 A composition as claimed in claim 4, wherein the hollow particulate material causes formation of a porous structure in the cement when set.
- 6 A method of designing a cement composition comprising: determining the temperature to which the composition will be exposed in situ; determining a stable, thermodynamic equilibrium composition of a $\text{CaO-Al}_2\text{O}_3\text{-SiO}_2\text{-H}_2\text{O}$ (CASH) mineral system in the [xonotlite/wollastonite]-grossulaire-anorthite or grossulaire-anorthite-quartz triangles of the Si-Ca-Al phase diagram, optionally including iron and/or magnesium, analogous to the cement when set, at the determined temperature; determining proportions of cement and mineral oxides required to provide a mixture having the determined composition; and defining a series of particulate materials of predetermined particle sizes and densities, comprising cement and mineral oxides in the determined proportions.

- 7 A method as claimed in claim 6, wherein the step of defining a series of particulate materials comprises determining three or more distinct particle size fractions.
- 8 A method of forming an item-comprising-placing-a-cement-composition in a form and allowing it to set, the cement composition comprising a mixture of cement and minerals contributing silicon, calcium and aluminium, and optionally iron and/or magnesium, to the mixture, wherein the composition of the mixture lies in the [xonotlite/wollastonite]-grossulaire-anorthite or grossulaire-anorthite-quartz triangles of the Si-Ca-Al phase diagram.
- 9 A method as claimed in claim 8, further comprising curing the item at an elevated temperature.

ABSTRACT

A method of designing a cement composition comprises determination of the temperature to which the composition will be exposed in situ; determination of a stable, thermodynamic equilibrium composition of a $\text{CaO-Al}_2\text{O}_3\text{-SiO}_2\text{-H}_2\text{O}$ (CASH) mineral system in the [xonotlite/wollastonite]-grossulaire-anorthite or grossulaire-anorthite-quartz triangles of the Si-Ca-Al phase diagram with a possible contribution of iron and/or magnesium, analogous to the cement when set, at the determined temperature; determining proportions of cement and mineral oxides required to provide a mixture having the determined composition; and defining a series of particulate materials of predetermined particle sizes and densities, comprising cement and mineral oxides in the determined proportions.




FIGURE 1




FIGURE 2a




FIGURE 2b




FIGURE 3




FIGURE 4




FIGURE 5

6/13




FIGURE 6




FIGURE 7





FIGURE 8



FIGURE 9




FIGURE 10




FIGURE 11




FIGURE 12




FIGURE 13




FIGURE 14




FIGURE 15




FIGURE 16




FIGURE 17




FIGURE 18




FIGURE 19



FIGURE 20




FIGURE 21




FIGURE 22




FIGURE 23




FIGURE 24



FIGURE 25




FIGURE 26




FIGURE 27



FIGURE 28




FIGURE 29

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☒ SKEWED/SLANTED IMAGES
- ☒ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.